



MagnaPrint® Crosslinker 400

MagnaPrint® Crosslinker 400 can be used to considerably reduce the time of curing inks. It is compatible with most MagnaPrint® printing systems.

MagnaPrint® Crosslinker 400 is particularly useful where dryers have insufficient dwell time.

Application

MagnaPrint® Crosslinker 400 can be used at varying concentrations, depending on the product into which it is to be added, but as a general rule do not exceed 20g/kg. Trials should be carried out under specific printing conditions to arrive at the correct addition level.

Once added to a print paste, MagnaPrint® Crosslinker 400 will remain active for a maximum of 8 hours. The print paste stability is not adversely affected and the system can be re-activated by a further addition of MagnaPrint® Crosslinker 400.

Minimum curing recommendation – 1½ minutes at 140°C (285°F)

SPECIFICATION



CURE TEMPERATURE

1½ minutes at 140°C (285°F)



STORAGE

In cool place properly closed:
>5°C (40°F) <25°C (77°F)



HEALTH & SAFETY

MSDS available upon request



CLEAN UP

Wash off screen using water and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.

