



MagnaTrans™ Adhesive 60

Printable Adhesive

MagnaTrans™ Adhesive 60 is a printable adhesive for use with the **MagnaTrans** range. Offering strong adhesion and a 60° C washfastness when applied to fabrics.

Application

Ensure your transfer print is completely dry before applying adhesive.

MagnaTrans Adhesive 60 is applied as the final layer to the finished transfer using 34 – 62T (86-158) screen mesh, with a 70-75° Shore Square Edge Squeegee.

Once applied, cure the transfer for 1-1.5 minutes at 140°C - 160°C (285°F - 320°F).

The finished transfer can be applied to the required substrate on a heat press at 165°C (329°F) for 12 seconds, 6 Bar pressure.

Once pressed, remove the transfer film from the print.

SPECIFICATION



FABRIC TYPES

Cotton, Poly-Cotton Blends, Polyester*



MESH

34 - 62T (86 - 158)



SQUEEGEE

70—75° Shore, Square Edge Squeegee



CURE TEMPERATURE

1-1.5 minutes at 140°C - 160°C (285°F - 320°F)



STORAGE

In cool place properly closed: >5°C (40°F) <25°C (77°F)



HEALTH & SAFETY

MSDS available upon request



CLEAN UP

Wash off screen using water and mild detergent

* With the use of MagnaTrans Migration Blocker.

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.