



MagnaPrint® Resist Paste

Ready to use print paste for wax batik effect

MagnaPrint® Resist Paste has been developed to simulate a wax Batik style of printing where a print is over dyed allowing the printed area to resist any of the colours from the dye bath.

It is designed to work best on cellulosic fibres which are subsequently dyed with direct or reactive dyestuffs.

Application

The fabric should be printed with the MagnaPrint® Resist Paste followed by drying and baked at 150°C (300°F) for 3 minutes.

If the style or design requires MagnaPrint® Resist Paste can be applied to the fabric by screen, paintbrush or even sprayed on to give the desired effect.

Please Note: Unless the fibre or yarn is totally covered with the print paste, dyestuff will fix to uncoated areas which will reduce the resist effect.

SPECIFICATION



FABRIC TYPES
Cotton



MESH
34-43T (86-110)



SQUEEGEE
Medium 65 Shore Rectangular



STENCIL
Water resistant emulsion



CURE TEMPERATURE
3 minutes at 150°C (300°F)



PIGMENT LOADING
Up to 6% MagnaPrint® Eco Pigments



ADDITIVES
Crosslinker 100



STORAGE
In cool place properly closed:
>5c (40F) <25c (77F)



HEALTH & SAFETY
MSDS available upon request



CLEAN UP
Wash off screen using water and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.