



## MagnaPrint® Crackle Range

### Vintage crackle effect - "Crack by hand"

The MagnaPrint® Crackle range is a fully aqueous ready to use printing paste. The range consists of a clear and a white ink designed to give a print effect with a "cracked" or "aged" appearance on knitted/stretchy fabrics.

MagnaPrint® Eco Pigments can be added in order to achieve a desired shade. The white may also be used in pure form to give a white print effect.

### Application

The MagnaPrint® Crackle range should be printed through an open mesh screen. The thicker the ink deposit the better the crack effect achieved.

After curing, the MagnaPrint® Crackle printed area should be stretched to achieve the "cracked" effect.

After printing, the garment / panel should be dried and cured, ideally for 2½ - 3 mins at 165°C (330°F).

### SPECIFICATION



#### FABRIC TYPES

Cotton / Poly Cotton blends



#### MESH

15 - 43T (38 - 110)



#### SQUEEGEE

Medium 65° Shore  
Rectangular



#### STENCIL

Water resistant emulsion



#### CURE TEMPERATURE

2½ - 3 minutes at 165°C  
(330°F)



#### PIGMENT LOADING

Up to 6% MagnaPrint®  
Eco Pigment



#### ADDITIVES

Retardent Gel, Crosslinker  
100



#### STORAGE

In cool place properly closed:  
>5°C (40F) <25°C (77F)



#### HEALTH & SAFETY

MSDS available upon  
request



#### CLEAN UP

Wash off screen using  
water and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.

